# (12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

### (19) World Intellectual Property Organization International Bureau



# 

(43) International Publication Date 31 July 2003 (31.07.2003)

PCT

### (10) International Publication Number WO 03/061829 A1

(51) International Patent Classification7: C01B 21/02, C01C 1/00

B01J 37/02.

(21) International Application Number: PCT/GB02/05761

(22) International Filing Date:

18 December 2002 (18.12.2002)

(25) Filing Language:

English

(26) Publication Language:

English .

(30) Priority Data: 0201378.7

22 January 2002 (22.01.2002) GB

(71) Applicants (for all designated States except US): BP CHEMICALS LIMITED [GB/GB]; Britannic House, 1 Finsbury Circus, London EC2M 7BA (GB). JOHN-SON MATTHEY P.L.C. [GB/GB]; 2-4 Cockspur Street, Trafalgar Square, London SW1Y 5BQ (GB).

(72). Inventors; and

- (75) Inventors/Applicants (for US only): BAKER, Michael, James [GB/GB]; 14 Derwent Close, Feltham, Middlesex TW14 9QL (GB). JOHNSTON, Peter [AT/GB]; 16 Gresley Lodge, Old North Road, Royston, Hertfordshire SG8 5AG (GB). MURPHY, Dennis [GB/GB]; 4 Stone Cottages, Newmarket Road, Moulton, Newmarket, Suffolk CB8 8QN (GB).
- (74) Agent: BROOKE, Caron; BP International Limited, Patents & Agreements, Chertsey Road, Sunbury on Thames, Middlesex TW16 7LN (GB).
- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IN, IS, JP, KE, KG, KP, KR, KZ, LC,

LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

#### Declarations under Rule 4.17:

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for the following designations AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HÜ, ID, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR. LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW, ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG)
- of inventorship (Rule 4.17(iv)) for US only

### Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

## (54) Title: PROCESS FOR THE PREPARATION OF A MICROSPHEROIDAL CATALYST

(57) Abstract: A process for impregnating microspheroidal catalyst support particles with at least one compound of a catalytically active group VIII noble metal, which process comprises the steps of: (a') impregnating the microspheroidal support particles by the incipient wetness technique with an aqueous solution of the at least one catalytically active group VIII noble metal, whilst agitating the support particles; and (b') drying the impregnated support particles produced in step (a')whilst agitating the impregnated support particles. The microspheroidal support particles are preferably silica, alumina, zirconia or mixtures thereof. Where the catalytically active group VIII noble metal is palladium, the process may be used to prepare a catalyst active for the fluid bed acetoxylation of ethylene to produce vinyl acetate.

